

TECHNICAL SPECIFICATIONS

Light transmittance	Transparent 85%, transparent green 76%, white 57%
Density	1,4 gr/cm
Hardness	40 Barcol
Water absorption rate	%(0,3-0,8) by weight
Light transmittance	%75-85
Tensile strength	720 kg/cm
Bending strength	1200 kg/cm
Pressure strength	1000 kg/cm
Flash Point	404,4 °C
Thermal conductivity coefficient	0,15-0,20 W/mK
Heat resistance	-40 °C -+120 °C
Expansion	9-25 mm X 10-6 mm/ °C